

Εμπορική ονομασία : **Τεχνομάραμα**

Προέλευση: Κίνα

Φυσικο-μηχανικές ιδιότητες - Ενδεικτικά εργαστηριακά αποτελέσματα (*):

Φαινόμενη πυκνότητα	2515 - 2525 kg/m ³	(EN 1936)
Αντοχή σε κάμψη (στεγνή κατάσταση)	22 - 23 MPa	(EN 12372)
Αντοχή σε θλίψη	105 - 125 MPa	(EN 1926)
Υδαταπορρόφηση	0,02 - 0,03 % κ.β.	(EN 13755)
Αντίσταση στην τριβή	22 - 26 mm (μήκος αύλακας)	(EN 14157-method A)
Αντίσταση στην ολίσθηση	SRV _{dry} : 50 SRV _{wet} : 16	(EN 14231)
Συντελεστής γραμμικής θερμικής διαστολής	13,5 - 22 (10 ⁻⁶ /°C)	(ISO 10545)
Σκληρότητα – κλίμακα Mohs	3,3 - 4	(SN/T 0308-93)
Αντίδραση στη φωτιά	Κλάση B – s 1, d 0	(EN 13501-1)
Περιεχόμενα ραδιονουκλίδια	Κλάση A (κανένας περιορισμός στη χρήση ως οικοδομικό /διακοσμητικό υλικό)	(GB 6566-2001)

(*) Τα στοιχεία αυτά βασίζονται σε πληροφορίες που μας παρέχει ο κατασκευαστής. Ωστόσο δεν αποτελούν εγγύηση για τα ειδικά χαρακτηριστικά μιας συγκεκριμένης παρτίδας προϊόντος και δε συνιστούν νομικά έγκυρη συμβατική σχέση.

Χαλάνδρι, 20/5/2016

AFFILIATE CODE: F615001
CERTIFICATE NO.: MN2009/0080XM-1
BOSS NO.: 11854697

Page 1 of 2

Testing Report for Submitted Sample

来样测试报告

SGS Job No. / SGS 工作单号: MN2009/0080XM

Declared Description / 样品名称: Artificial Stone / 人造大理石

Sample Remitted Date / 到样日期: May 12, 2009 / 2009 年 5 月 12 日

Testing Period / 测试周期: May 12 ~ June 8, 2009 / 2009 年 5 月 12 日~6 月 8 日

This is to report that we, SGS-CSTC Standards Technical Services Co., Ltd. Xiamen, at the request of Messrs. ===== LTD., who submitted us samples declared description as above which were sent to our laboratory for testing, we quote the results as follows:

兹证明我司通标标准技术服务有限公司厦门分公司受福建省泉州市鹏翔岗石有限公司委托, 对其来样进行测试, 结果引用如下:

1	Test Item 测试项目	Test Method 测试方法	Test Result 测试结果
1	Length (mm) 长	EN 13373:2003	500.17
	Width (mm) 宽	EN 13373:2003	500.17
	Thickness (mm) 厚	EN 13373:2003	18.16
	Remark: Sample nominal size: 500×500×18mm 备注: 样品公称尺寸: 500×500×18mm		
2	Flatness (%) 平整度	EN 13373:2003	0.026
3	Visual appearance 外观检查	EN 12057:2004	No defect and cracks were found on the surface of the sample. The test sample shows no visible difference in color with the reference sample. 表面无缺陷及裂纹, 在色泽上与参照样品无差别。
4	Apparent density (kg/m3) 表观密度	EN 1936:2006	2520
5	Water absorption (%) 吸水率	EN 13755:2008	0.02

***** To be continued*****



AFFILIATE CODE: F615001
CERTIFICATE NO.: MN2009/0080XM-1
BOSS NO.: 11854697

Page 2 of 2

1	Test Item 测试项目	Test Method 测试方法	Test Result 测试结果	
6	Flexural strength (dry), (MPa) 干燥弯曲强度	EN 12372:2006	22.8	
7	Compressive strength (MPa) 抗压强度	EN 1926:2006	125.4	
8	Mohs hardness 莫氏硬度	SN/T 0308-93	3.3	
9	Coefficient of liner thermal expansion (10 ⁻⁶ /°C) 线性热膨胀系数	ISO 10545:1994	22.1	
10	Abrasion resistance 耐磨损	EN 14157:2004	The mean length of the groove: 22.0mm 凹槽平均长度: 22.0mm	
11	Slip resistance 抗滑移性	EN 14231:2003	SRVdry: 50 干防滑系数 SRVwet: 16 湿防滑系数	
12	Limit of radionuclides in building materials 建筑材料放射性核素限量	Item 项目	Result 结果	Class A Requirement A 类材料要求
		Internal exposure index 内照射	0.033	≤1.0
		External exposure index 外照射	0.027	≤1.3
		Remark 备注	A Grade decorating material is not limited when producing, selling and using. A 类装修材料生产、销售与使用范围不受限制。	

This report reflects our findings for analyzing of the submitted sample only, and does not refer to any matters or evidence for any shipment. This report does not for L/C negotiation.

The information stated in this report (or certificate) is derived from the results of inspection or testing procedures carried out in accordance with the instructions of our Client, and/or our assessment of such results on the basis of any technical standards, trade custom or practice, or other circumstances which should in our professional opinion be taken into account.

*****END*****

Xiamen, June 10, 2009

2009年6月10日

SGS-CSTC Standards Technical Services Co., Ltd.

通标标准技术服务有限公司厦门分公司

中国·北京
海淀区阜成路 73 号
世纪裕惠大厦 16 层
邮编: 100036
电话: (86-10) 6845 6699
传真: (86-10) 6845 7979

Page 1 of 5

来样测试报告

Testing Period / 测试周期 : May 12 ~ June 10, 2009 / 2009 年 5 月 12 日~6 月 10 日

兹证明我司通标标准技术服务有限公司厦门分公司受福建省泉州市鹏翔岗石有限公司委托，对其来样进行测试，结果引用如下：

1. Test reference / 试验方法

EN 13501-1:2007 建筑制品和构件的火灾分级 第 1 部分: 用对火反应试验数据的分级进行分级

1. EN 13823:2002 Reaction to fire tests for building products - Building products excluding floorings exposed to the thermal attack by a single burning item.
EN 13823:2002 建筑制品对火反应试验—不含铺地材料的建筑制品单体燃烧试验。
2. EN ISO 11925-2: 2002 Reaction to fire tests - Ignitability of building products subjected to direct impingement of flame - Part 2: Single-flame source test.
EN ISO 11925-2:2002 对火反应试验 - 受到直接火焰撞击的建筑制品的可燃性—第 2 部分：小火焰源试验规定的试验方法。

II. Product details / 制品描述

Details of the nature and use of the product 样品信息	Countertops, wall claddings, flooring, etc. 台面板, 装饰墙面地面等
--	---

备注: 以上样品信息由客户提供。

III. Test results / 测试结果

Test method 试验方法	Parameter 参数	Specimen number 样品数量	Results 试验结果
EN 13823	FIGRA (W/s)	3	4
	LFS < edge of specimen		YES
	LFS < 试样边缘		是
	THR _{600s} (MJ)		0.23
	SMOGRA (m ² /s ²)		Not detected 没有发现
	TSP _{600s} (m ²)		0
EN ISO 11925-2 Exposure = 30s 点火时间 = 30秒	Flaming particles or droplets 燃烧滴落物/微粒	6	NO / 否
	Fs ≤ 150mm Ignition of the filter paper 是否引燃滤纸		YES / 是 NO / 否

IV. Classification / 分级

This classification has been carried out in accordance with EN 13501-1:2007.

试验制品燃烧性能等级以及产烟量和燃烧滴落物的附加等级按EN13501-1:2007的相关条款判定。

Conclusion: The product, Artificial Stone, classification is as following.

结论: 该制品“人造大理石”分级结果如下:

Fire behaviour 燃烧性能	Smoke production 产烟量	Flaming droplets 燃烧滴落物
B	s 1	d 0
Reaction to fire classification: B - s 1, d 0 燃烧性能等级: B - s 1, d 0		

Remark: The classes with their corresponding fire performance are given in annex A.

备注: 分级参数表见附录A。

Statement: The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

陈述: 在特定的试验条件下, 试验结果与试样的性能有关; 试验结果不能作为评估制品在实际使用条件下潜在火灾危险性的唯一依据。

Annex A / 附录 A

Classes of reaction to fire performance for construction products excluding floorings and linear pipe thermal insulation products

建筑材料及制品 (铺地材料材料除外) 燃烧性能分级

Class 等级	Test method 测试标准	Classification criteria 分级判据	Additional classification 附加分级
A1	EN ISO 1182 ^a and	$\Delta T \leq 30^\circ\text{C}$, and $\Delta m \leq 50\%$, and $t_f = 0$ (i.e. no sustained flaming)	-
	EN ISO 1716	$PCS \leq 2.0 \text{ MJ/kg}^a$ and $PCS \leq 2.0 \text{ MJ/kg}^{bc}$ and $PCS \leq 1.4 \text{ MJ/m}^2$ and $PCS \leq 2.0 \text{ MJ/kg}^e$	-
A2	EN ISO 1182 ^a or	and $\Delta T \leq 50^\circ\text{C}$, and $\Delta m \leq 50\%$, and $t_f \leq 20 \text{ s}$	-

	EN ISO 1716	PCS $\leq$ 3.0MJ/kg ^a and PCS $\leq$ 4.0MJ/m ² ^b and PCS $\leq$ 4.0MJ/m ² ^d and PCS $\leq$ 3.0MJ/kg ^e	
	EN 13823	FIGRA $\leq$ 120W/s and LFS<edge of specimen and THR _{600s} $\leq$ 7.5MJ	Smoke production ^f and Flaming droplets/particles ^g 产烟量 ^f 且 燃烧滴落物/微粒 ^g
B	EN 13823 and EN ISO 11925-2 ¹ Exposure=30s / 点火时间=30秒	FIGRA $\leq$ 120W/s and LFS<edge of specimen and THR _{600s} $\leq$ 7.5MJ	Smoke production ^f and Flaming droplets/particles ^g 产烟量 ^f 且 燃烧滴落物/微粒 ^g
		F _s $\leq$ 150mm within 60 s	
C	EN 13823 and EN ISO 11925-2 ¹ Exposure=30s / 点火时间=30秒	FIGRA $\leq$ 250W/s and LFS<edge of specimen and THR _{600s} $\leq$ 15MJ	Smoke production ^f and Flaming droplets/particles ^g 产烟量 ^f 且 燃烧滴落物/微粒 ^g
		F _s $\leq$ 150mm within 60 s	
D	EN 13823 and EN ISO 11925-2 ¹ Exposure=30s / 点火时间=30秒	FIGRA $\leq$ 750W/s	Smoke production ^f and Flaming droplets/particles ^g 产烟量 ^f 且 燃烧滴落物/微粒 ^g
		F _s $\leq$ 150mm within 60 s	
E	EN ISO 11925-2 ¹ Exposure=15s / 点火时间=15秒	F _s $\leq$ 150mm within 20 s	flaming droplets/particles ^h 燃烧滴落物/微粒 ^h
F	No performance determined / 无性能要求		

^a For homogeneous products and substantial components of non-homogeneous products.

a: 匀质制品和非匀质制品的主要组份;

^b For any external non-substantial component of non-homogeneous products.

b: 非匀质制品的外部次要组份;

^c Alternatively, any external non-substantial component having a PCS $\leq$ 2.0 MJ/m², provided that the product satisfies the following criteria of EN 13823: FIGRA $\leq$ 20 W/s, and LFS < edge of specimen, and THR_{600s} $\leq$ 4.0 MJ, and s1, and d0.

c: 另一个可选择的判据是: 对 PCS $\leq$ 2.0MJ/m² 的外部次要组份, 则要求满足 FIGRA $\leq$ 20W/s、LFS < 试样边缘、THR_{600s} $\leq$ 4.0MJ、s1和d0;

^d For any internal non-substantial component of non-homogeneous products.

d: 非匀质制品的任一内部次要组份;

^e For the product as a whole.

e: 整体制品;

^f In the last phase of the development of the test procedure, modifications of the smoke measurement system have been introduced, the effect of which needs further investigation. This may result in a modification of the limit values and/or parameters for the evaluation of the smoke production.

f: 在试验程序的最后阶段, 需对烟气测量系统进行调整, 烟气测量系统的影响需进一步研究。由此导致评价产烟量的参数或极限值的调整。

s1 = SMOGRA $\leq$ 30m²/s² and TSP_{600s} $\leq$ 50m²; s2 = SMOGRA $\leq$ 180m²/s² and TSP_{600s} $\leq$ 200m²; s3 = not s1 or s2
s1=SMOGRA $\leq$ 30m²/s²且TSP_{600s} $\leq$ 50m²; s2=SMOGRA $\leq$ 180m²/s²且TSP_{600s} $\leq$ 200m²; s3=未达到s1或s2;

^g d0 = No flaming droplets/ particles in EN 13823 within 600 s;

d1 = no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600 s;

d2 = not d0 or d1.

Ignition of the paper in EN ISO 11925-2 results in a d2 classification.

g: d0=按 EN 13823 规定, 600s 内无燃烧滴落物/微粒;

d1=按 EN 13823 规定, 600s 内燃烧滴落物/微粒持续时间不超过 10s;

d2=未达到 d0 或 d1;

按照 EN ISO 11925-2 规定, 过滤纸被引燃, 则该制品为 d2 级;

^h Pass = no ignition of the paper (no classification);

Fail = ignition of the paper (d2 classification).

AFFILIATE CODE: F615001
CERTIFICATE NO.: MN2009/0080XM-4
BOSS NO.: 11854697

Page 4 of 5

h: 通过=过滤纸未被引燃;

未通过=过滤纸被引燃 (d2级);

Under conditions of surface flame attack and, if appropriate to the end-use application of the product, edge flame attack
i: 火焰轰击制品的表面和 (如果适合该制品的最终应用) 边缘。

1. EN 13823: 2002

I. Test reference / 测试标准

This test is conducted as per EN 13823:2002 Reaction to fire tests for building products - Building products excluding floorings exposed to the thermal attack by a single burning item.

EN 13823:2002 建筑制品对火反应试验—不含铺地材料的建筑制品单体燃烧试验

II. Sample details / 试样信息:

Material 材质	Artificial Stone 人造大理石		
Specimen size (mm) 样品尺寸	Long wing: 1500×1000×18.5; Short wing: 1500×495×18.5 长翼: 1500×1000×18.5; 短翼: 1500×495×18.5		
Descriptions (including the substrate, mounting of specimen, etc) 描述 (包括试样基材、安装等样品详情)	i. Calcium silicate board, with its density 900kg/m ³ , thickness 9mm, is as the substrate of the specimen. 厚度为9毫米, 密度为900kg/m ³ 的硅酸钙作为测试基材		
	ii. The specimens are fixed mechanically to the substrate. 试样采取机械方式固定于基材上		
	iii. The specimens tested with horizontal joint and vertical joint in the long wing. 在试样长翼上设有水平和垂直接缝		
	iv. The specimens tested with a 40mm cavity between substrate and backing board. 试验基材与背板之间的间隙为40毫米		
Precondition 试样调节	Temperature (°C) 温度	Humidity (%) 相对湿度	Duration (h) 时间
	23±2	50±5	360

Remark: Test specimens shall be conditioned at least 48 h before testing, until constant mass is achieved.

备注: 试样至少调节 48 小时直到质量平衡。

III. Test results / 测试结果

Items 项目	1 试样1	2 试样2	3 试样3	Average 平均值
FIGRA _{0.2MJ} (W/s)	3	5	3	4
FIGRA _{0.4MJ} (W/s)	—	—	—	—
THR _{600s} (MJ)	0.2	0.3	0.2	0.23
SMOGRA (m ² /s ²)	Not detected 没有发现	Not detected 没有发现	Not detected 没有发现	Not detected 没有发现
TSP _{600s} (m ²)	0	0	0	0
LFS < edge of specimen (yes/no) LFS < 试样边缘	YES 是	YES 是	YES 是	YES 是
Flaming particles or droplets 燃烧的碎块或滴落物	NO 否	NO 否	NO 否	NO 否

2. EN ISO 11925-2:2002

I. Test reference / 测试标准

AFFILIATE CODE: F615001
CERTIFICATE NO.: MN2009/0080XM-4
BOSS NO.: 11854697

Page 5 of 5

This test is conducted as per EN ISO 11925-2:2002 Reaction to fire tests - Ignitability of building products subjected to direct impingement of flame - Part 2: Single-flame source test.
EN ISO 11925-2:2002 对火反应试验—受到直接火焰撞击的建筑制品的可燃性 - 第2部分: 小火焰源试验

II. Sample details / 试样信息

Material 材质	Artificial Stone 人造大理石			
Size of sample (mm) 样品尺寸	250×90×18.5			
Precondition 试样调节	Temperature (°C) 温度 23±2	Humidity (%) 湿度 50±5	Duration (h) 时间 360	
Flame application time 点火时间	30 s 30秒			

III. Test Results / 测试结果

(A) Face ignition / 表面点火

Parameter 参数	1	2	3
Occurrence of ignition (Yes/No) 是否发生点燃	NO	NO	NO
Whether flame reaches 150mm 火焰是否达到150mm处	NO	NO	NO
Time to reach 150mm 到达150mm的时间	--	--	--
Ignition of the filter paper (Yes/No) 是否点燃滤纸	NO	NO	NO

(B) Bottom edge ignition / 边缘点火

Parameter 参数	1	2	3
Occurrence of ignition (Yes/No) 是否发生点燃	NO	NO	NO
Whether flame reaches 150mm 火焰是否达到150mm处	NO	NO	NO
Time to reach 150mm 到达150mm的时间	--	--	--
Ignition of the filter paper (Yes/No) 是否点燃滤纸	NO	NO	NO

This report reflects our findings for analyzing of the submitted sample only, and does not refer to any matters or evidence for any shipment. This report does not for L/C negotiation.

The information stated in this report (or certificate) is derived from the results of inspection or testing procedures carried out in accordance with the instructions of our Client, and/or our assessment of such results on the basis of any technical standards, trade custom or practice, or other circumstances which should in our professional opinion be taken into account.

*****END*****

Xiamen, June 17, 2009

SGS-CSTC Standards Technical Services Co., Ltd.

2009年6月17日

通标标准技术服务有限公司厦门分公司