

Commercial name: **SINAI PEARL marble**

Indicative material's picture

Country of origin: Egypt

Mineralogical composition:
Calcite 100%



Physico-mechanical properties - Indicative lab test results (*):

Apparent density	2570 kg/m ³	EN 1936
Flexural strength	14 MPa	EN 12372
Uniaxial compressive strength	155 MPa	EN 1926
Water absorption at atmospheric pressure	1,3 %	EN 13755

(*) This information is based on our present knowledge out of laboratory tests and other information sources. However, this shall not constitute a guarantee for any specific batch of stone and shall not establish a legally valid contractual relationship.

Halandri, 30/7/2021