

Commercial name: **NEW IMPERIAL RED granite**

Indicative material's picture:

Country of origin: India



Physico-mechanical properties - Indicative lab test results (*):

Apparent density	2600 - 2700 kgr/m ³	(EN 1936)
Flexural strength	15 - 20 MPa	(EN 12372)
Compressive strength	190 - 250 MPa	(EN 1926)
Water absorption	0.05 – 0.15 % wt.	(EN 13755)

() This information is based on our present knowledge out of laboratory tests and other information sources.. However, this shall not constitute a guarantee for any specific batch of stone, and shall not establish a legally valid contractual relationship.*

Halandri, 3/9/2014