

Commercial name: **YELLOW CALIFORNIA granite**

Indicative material's picture:

Country of origin: Brazil



Physico-mechanical properties - Indicative lab test results (*):

Apparent density	2630 kg/m ³	(EN 1936)
Open porosity	0,6 % vol	(EN 1936)
Water absorption	0.25 – 0.40 % wt.	(EN 13755)
Flexural strength	9 - 10 MPa	(EN 12372)
Compressive strength	140 - 170 MPa	(EN 1926)

() This information is based on our present knowledge out of laboratory tests and other information sources.. However, this shall not constitute a guarantee for any specific batch of stone, and shall not establish a legally valid contractual relationship.*

Halandri, 3/9/2014