

Commercial name: **YELLOW TOPAZIO LIGHT granite**

Indicative material's picture:

Country of origin: Brazil



## Physico-mechanical properties - Indicative lab test results (\*):

|                      |                               |            |
|----------------------|-------------------------------|------------|
| Apparent density     | 2680 - 2720 kg/m <sup>3</sup> | (EN 1936)  |
| Water absorption     | 0.14 % wt.                    | (EN 13755) |
| Flexural strength    | 10 - 20 MPa                   | (EN 12372) |
| Compressive strength | 150 - 160 MPa                 | (EN 1926)  |

*(\*) This information is based on our present knowledge out of laboratory tests and other information sources.. However, this shall not constitute a guarantee for any specific batch of stone, and shall not establish a legally valid contractual relationship.*

Halandri, 3/9/2014